

# Vinyl-backed Tile, Planks, Rolls

US Testing

| WEAVE                | SIZE                              | WEIGHT<br>(+/- 10%)<br>OZ/Y <sup>2</sup> | THICKNESS<br>(+/- 10%)<br>INCHES |
|----------------------|-----------------------------------|--|----------------------------------|
| Basketweave, FG-Core | 18" x 18", 6" x 36", or 72" Rolls | 120.5                                    | 0.13                             |
| Bouclé               | 18" x 18", 6" x 36", or 72" Rolls | 115.7                                    | 0.13                             |
| Dart                 | 18" x 18", 6" x 36", or 72" Rolls | 120.5                                    | 0.13                             |
| Ikat                 | 18" x 18", 6" x 36", or 72" Rolls | 117.5                                    | 0.12                             |
| Plaid                | 18" x 18", 6" x 36", or 72" Rolls | 117.5                                    | 0.12                             |
| Reed                 | 18" x 18", 6" x 36", or 72" Rolls | 114.2                                    | 0.14                             |
| Rib Weave            | 18" x 18", 6" x 36", or 72" Rolls | 123.0                                    | 0.16                             |
| Savile               | 18" x 18", 6" x 36", or 72" Rolls | 113.2                                    | 0.13                             |
| Shade                | 18" x 18", 6" x 36", or 72" Rolls | 117.0                                    | 0.13                             |
| Speckle              | 18" x 18", 6" x 36", or 72" Rolls | 117.7                                    | 0.13                             |

| TEST CONDUCTED                         | TEST NAME       | RESULT           |
|--|-----------------|------------------|
| Colorfastness - Light                  | AATCC 16E       | 5                |
| Colorfastness - Nitrogen               | AATCC 164       | 5                |
| Colorfastness - Light                  | AATCC 129       | 5                |
| Accelerated Heat Aging                 |                 | 5                |
| Methamine Pill Text                    | CSPC FF1-70     | 8/8 Pass         |
| Critical Radiant Flux                  | ASTM E648       | Class 1          |
| Optical Smoke Density                  |                 |                  |
| Flaming @ 4 min.                       | ASTM E662-03    | < 400            |
| Floorwear                              | Contract Walker | 5 Excellent      |
| Hexapod Walker                         | ASTM D5252      | Heavy Commercial |
| Static Generator                       | AATCC 134       | < 2.0 kv         |
| Dimensional Stability                  | 2199-99         | < 0.1%           |
| Compression Recovery<br>after 96 hours | Static Load     | 95%              |
| Resistance to Chemicals                | ASTM F925       | No Effect        |
| Slip Resistance                        | ASTM C1028      | > 0.72           |
| Impact Sound Transmission              | ASTM E989-89    | ΔIIC 18          |
| Aachen Stability Test                  | ASTM D7570      | < 0.05%          |
| Aachen Curl and Doming Test            | ASTM D7570      | < 0.05%          |

| PRODUCT | UNITS/PACK | AREA/PACK      |
|---------|------------|----------------|
| TILE    | 20 TILES   | 45 SQUARE FEET |
| PLANKS  | 30 PLANKS  | 45 SQUARE FEET |

| PRODUCT | WIDTH    | LENGTH                                     |
|---------|----------|--|
| ROLLS   | 72" WIDE | UP TO 150' LONG (CUSTOM LENGTHS AVAILABLE) |