

# Custom Floor Mats

US Testing

WEAVE	WIDTH	WEIGHT (+/- 10%) OZ/Y <sup>2</sup>	THICKNESS (+/- 10%) INCHES
Bamboo	72", or max 18' with seams	41.1	0.15
Basketweave, FG-Core	72", or max 18' with seams	51.5	0.15
Basketweave, P-Core	72", or max 18' with seams	46.3	0.14
Bouclé	72", or max 18' with seams	46.5	0.15
Dart	72", or max 18' with seams	51.5	0.15
Frost	72", or max 18' with seams	59.1	0.19
Heddle	72", or max 18' with seams	58.7	0.18
Ikat	72", or max 18' with seams	48.7	0.15
Mini Basketweave	72", or max 18' with seams	46.6	0.14
Mixed Weave	72", or max 18' with seams	43.7	0.15
Mosaic	72", or max 18' with seams	42.8	0.14
Plaid	72", or max 18' with seams	43.2	0.14
Reed	72", or max 18' with seams	45.2	0.16
Rib Weave	72", or max 18' with seams	54.0	0.18
Savile	72", or max 18' with seams	48.0	0.13
Scout	72", or max 18' with seams	43.2	0.14
Shade	72", or max 18' with seams	47.7	0.15
Speckle	72", or max 18' with seams	48.7	0.16
Wave	72", or max 18' with seams	42.5	0.14

TEST CONDUCTED	TEST NAME	RESULT
Critical Radiant Flux	ASTM E648	Class 1
Compression Recovery after 96 hours	Static Load	< 94%
Surface Flammability	ASTM DOC FF-70	Pass